



Technical datasheet No.: **1318.6**

Product: POLYMAR® T 22

Article No.: 8831 5340

Type of coating and finish			
Type of coating	PVC		
Burning behaviour	ISO 3795 <100 mm/min.		
Total Weight	22.4	oz./sq.yd.	ASTM D-751.10
Strip Tensile (warp/weft)	425 / 390	lbs. / in.	ASTM D-751 Procedure B
Tongue Tear	110 / 110	lbs.	ASTM D-751 (8" x 10") Specimen
Adhesion	11	lbs. / in.	ASTM D-751 RF Weld
Low Temperature	-40	°F	ASTM D-2136
High Temperature	158	°F	PA 07.04 (intern)
Light fastness	>6	Note, Value	ISO 105 B02
Abrasion (TABER)	500	Cycles	ASTM D 3389-10 (Taber, H-22, 1000 grams)
Crack resistance	no cracks	100000 x	DIN 53359 A
Base fabric			
Material	PES		DIN EN ISO 2076
Yarn count	1000	den.	DIN EN ISO 2060
Weave	P 2/2		

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.