



Technical datasheet No.: **1179.3**

Product: POLYMAR® mower apron

Article No.: 7601 5340

Type of coating and finish			
Type of coating	PVC		
Burning behaviour	ISO 3795 <100 mm/min.		
Total Weight	40 oz./sq.yd.	ASTM D-751.10	
Strip Tensile (warp/weft)	425 / 390 lbs. / in.	ASTM D-751 Procedure B	
Tongue Tear	110 / 110 lbs.	ASTM D-751 (8" x 10") Specimen	
Adhesion	11 lbs. / in.	ASTM D-751 RF Weld	
Low Temperature	-30 °F	ASTM D-2136	
High Temperature	158 °F	LB 3.15	
Light fastness	>6 Note, Value	ISO 105 B02	
Crack resistance (z)	no cracks	@ 100000 x	DIN 53359 A
Base fabric			
Material	PES	ISO 2076	
Yarn count	1000 den.	ISO 2060	
Weave	P 2/2		

We believe this information is the best currently available on the subject. It is offered as a possible suggestion and guideline in experimentation you may undertake along these lines. It is subject to revision as additional knowledge and experiences are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.